

COMBAT 777

MOULD-RESISTANT EMULSION PAINT FOR INTERIORS

code 4870777

DESCRIPTION

COMBAT 777 is an emulsion paint for interior use with a certain degree of breathability, especially formulated to prevent on interior surfaces subjected to condensation and damp,

The product has a long-lasting effect, and does not alter the original appearance of the surface.

In addition, COMBAT 777 offers good hiding power, a high level of breathability and ease of use.

INSTRUCTIONS FOR USE

May be applied on:

- New and old plasters based on hydraulic binders.
- Concrete surfaces.
- Gypsum and gypsumboard surfaces.
- Old paints and wall coatings that are organic or mineral in nature, dry, compact, absorbent and cohesive.
- Mineral conglomerates of various kinds, as long as they are absorbent.

Surfaces should be adequately prepared by following the instructions given in the paragraph 'PREPARING THE SURFACE'.

Do not apply on freshly painted surfaces.

TECHNICAL SPECIFICATIONS

- Nature of the binder: vinylversatate copolymer in emulsion.
- Specific gravity per UNI EN ISO 2811-1: 1.70 ± 0.05 kg/l
- Viscosity per UNI 8902: 4000 ± 1600 cps at 25 °C
- Gloss per EN ISO 2813: 5-10, matt
- *Anti-mold efficacy per UNI 9805: 0 = no development
- *Resistance to fungi per UNI EN 15457: 0 = no development
- Drying time (at 25 °C and 65% R.H.): to touch 30 minutes; to recoat after 4 hours.

*Test report n° 55406 and n° 68308 issued by THOR SPECIALTIES of Besnate (Va).

PREPARING THE SURFACE

Wall and ceiling surfaces:

- Make sure that the surface is thoroughly dried and aged. Resurface or consolidate using specific products if necessary.
- If mold is present, treat the surface with COMBAT 222 cleanser code 4810222, and with COMBAT 333 reconstruction code 4810333. To protect the wall from mold formation add COMBAT 444 code 4810444 sanitizer to the product.
- Brush or wash to remove any efflorescence and any old peeling paint. Completely eliminate any raised layers of lime-based or tempera paints.
- Remove any dust, smog or other deposits by brushing.
- Level any irregularities in the surface and treat holes, cracks, crevices and gaps with TAMSTUCCO 9400006/9410110; sand putty and touch-ups with sandpaper.
- Use adequate sealants to seal any cracks.

- Smooth if necessary with RASAMIX 9440160 or with BETOMARC 9450150 or RASOMARC 9500150 according to the type of support.

- On a clean, dry surface apply one coat of IDROFIS 4700006 acrylic water-based wall fixative or ATOMO 8840001 micronized solvent-free fixative. On gypsumboard, apply the specific fixative PREPARA 4710019 pigmented fixative. In the presence of thin layers of old tempera or chalking paints, apply one coat of solvent-based wall fixative ISOMARC 4410111 or ATOMO 8840001 micronized solvent-free fixative.

- Apply COMBAT 777.

*(The dilution of the fixative and amounts to be applied depend on the absorption of the support surface, and must be determined through preliminary tests on the specific support surface - See the relevant technical data sheet).

APPLICATION INSTRUCTIONS

- Air and support surface conditions:

Air temperature: Min. +8 °C / Max. +35 °C

Relative environmental humidity: <75%

Support surface temperature: Min. +5 °C / Max. +35 °C

Moisture level of the support surface: <10%

- Tools: brush, roller, spray gun or airless.

- N. of coats: 2 coats.

- Diluting: with water. First coat at 40%; second coat at 20-30%.

- When airless spraying thinning varies depending on the unit and operating pressure used.

- Tools should be cleaned immediately after use using water.

- Indicative spreading rate: 7-8 sqm/l per coat based on smooth surfaces featuring average absorption. It is advisable to determine the actual spreading rate by carrying out a preliminary test on the specific surface.

TINTING

The product may be tinted by means of the Color Matching System.

The product may also be tinted using BRAVOCASA TINTE COLORANTI series 408P (in light shades only) and COLORADO series 548 colorants.

When using multiple batches it is recommended to remix the various products together to avoid slight differences in shading.

STORAGE

Maximum temperature for storage stability: +30 °C

Minimum temperature for storage stability: +5 °C

The product should be preferably used within 2 years from date of manufacture when stored in original unopened containers and in appropriate temperature conditions.

SAFETY RULES

Limit value EU (Dir. 2004/42/EC)

Cat. A/a: Matt coatings for interior walls and ceilings (gloss \leq 25@60°) (water-base): 30 g/l (2010)

The product contains max: 30 g/l VOC

COMBAT 777

MOULD-RESISTANT EMULSION PAINT FOR INTERIORS

code 4870777

Use the product according to current standards of hygiene and safety after use, do not litter containers, allow the residue to dry and treat them as special waste. Do not empty into drains, water courses or onto the ground. For more information see the safety data sheet.

SPECIFICATION ITEM

Applications, on previously prepared surfaces, of mould-resistant emulsion paint COMBAT 777 cod. 4870777, with a base of vinylversatic resins dispersed in water and additives preserving the surface against mould growth, with the application of at least 2 coats of a quantity determined by the level of absorption of the surface.

Supply and application of the material €. per m2.

SAN MARCO GROUP guarantees that the information herein is provided to the best of its technical and scientific knowledge and based on its experience; nonetheless, the company may not be held liable for the results obtained using these products, as application conditions are beyond its control. It is recommended to always make sure that the product is suited to each specific instance. The present sheet voids and replaces any previously existing sheets. For further technical information call the technical service +39 041 4569322.